



CONMARBLE
NATURAL FINISHES



VOC CONTENT TEST REPORT

CEMHER HYDROPRIMER

Full laboratory VOC content test report

A CONMARBLE NATURAL FINISHES SYSTEM · LIME PLASTER

PRODUCT MANUFACTURED BY

CEMHER

Cemher · Spain

DOCUMENT ISSUED BY

Applus Laboratories / LGAI Technological Center S.A. — DANAK-accredited lab reg. 522

Reproduced in full and unaltered. Transmitted by Building Layers by Conmarble as supplier and approved applicator.

[VIEW OUR PROFILE](#)

[CONMARBLE.COM](https://conmarble.com)

BUILDING LAYERS BY CONMARBLE – Tabqat Albunyan Company For Contracting - CR: 7041240065
Showroom Location : Al Urubah Road, Al Olaya, PMV69+7V, City of Riyadh 12333, Saudi Arabia
Email: ahmad@conmarble.com, Insta: @conmarble, Tel: KSA +966 547 888 809 · QA +974 5573 7641

JULY 2026

Eurofins Product Testing, Cosmetics & Personal Care Spain, S.L.U.
C/ Ausias March, 148-150
08013 Barcelona
SPAIN

Eurofins Product Testing Denmark A/S
Smedeskovvej 38
8464 Galten
Denmark

CustomerSupport@eurofins.com
www.eurofins.com

Applicant:
KILNHER
C/. Llanterners, 44; P.I. La Figuera
46970 - Alaquas (Valencia)
Spain

TEST REPORT

VOC Content

9 April 2024

1 Sample Information

Sample name	HYDROPRIMER
Sample no.	392-2024-00140102
Stated production date	26/02/2024
Batch No.	24F02260206
Sample reception	15/03/2024

2 Brief Evaluation of the Results

Regulation or protocol	Conclusion	Version of regulation or protocol
SCAQMD Rule 1113	Pass	February 2016
LEED v4.1 (VOC Content)	Pass	July 2023

Full details based on the testing and direct comparison with limit values are available in the following pages
Regarding pass/fail decision rule please see appendix



Janne Rothmann Norup
Analytical Service Manager

3 Applied Test Methods

3.1 General Test References

Regulation, protocol or standard	Scope	Version
SCAQMD Rule 1113	Architectural coatings	February 2016

3.2 Specific Laboratory Sampling and Analyses

Test	Regulation, protocol or standard	Version	Internal SOP	Limit of detection [g/L]	Uncertainty U _{max} %
Solids Content	ASTM D2369	2020	71 M 544830	1	10
VOC	ASTM D2369/SCAQMD Rule 1113	2020/2016	71 M 544830	1	10
Water content *	Karl-Fischer titration	-	71 M 543150	0.5 % (w/w)	10
Density *	Internal method	-	71 M 543130	-	10

3.3 Preparation of the Test Specimen

The sample was homogenised and applied directly onto the test dish.

4 Results

4.1 VOC content

	Remarks on the test results	Results	Unit
Density *	Tested by the lab	1.02	g/mL
Water content *	Tested by the lab	64.7	% (w/w)
Exempt compounds *	Assumed to be 0	0	% (w/w)
Solids Content	Tested by the lab	42.1	% (w/w)
VOC content (less water)	Calculated based on the results above	< 1	g/L

4.2 Comparison with Limit Values of VOC Content (less Water)

Parameters	Results [g/L]	Product type	Regulation or protocol	VOC limit [g/L]
VOC content	< 1	Primers, sealers and undercoaters	SCAQMD Rule 1113	100

5 Appendices

5.1 How to Understand the Results

5.1.1 Acronyms Used in the Report

<	Means less than
>	Means bigger than
*	Not a part of our accreditation
±	Please see section regarding uncertainty in the Appendices
1	Analysed by another Eurofins laboratory

5.2 Description of VOC Content Test

5.2.1 Testing of VOC

Volatile content of the sample was determined gravimetrically by heating to 110 °C in 60 minutes. Multicomponent products are mixed according to the manufacturer's instructions and allowed to cure before heating.

The result is the average of two replicates. The result was calculated as:

$$VOC = \frac{([g \text{ All Volatiles}] - [g \text{ Water}] - [g \text{ Exempt Compounds}])}{([liter \text{ Material}] - [liter \text{ Water}] - [liter \text{ Exempt Compounds}])}$$

5.2.2 Testing of Density

The density was calculated using gravimetric and volumetric determination. The result is the average of three determinations.

5.3 Uncertainty of the Test Method

Um(%): The expanded uncertainty Um is equal to 2 x RSD%.

5.4 Decision Rules

Eurofins Product Testing A/S, declare statement of conformity based on the "Binary Statement for Simple Acceptance Rule" described in ILAC's "Guidelines on decision Rules and Statements of Conformity" ILAC-G8:09/2019.

This means that results above the detection limit are always reported with two significant digits. Results are evaluated with the same number of significant digits as the corresponding limit values, and conformity is based on results being less than or equal to limit values.

For limit values with more than two significant digits, the third digit will be used to confirm whether a result is below or equal to the limit value. It will always be indicated in the evaluation table if this expanded evaluation is performed.

For further information, please visit www.eurofins.dk/product-testing/om-os/beslutningsregler/

5.5 Version History

Report date	Report number	Modification
09/04/2024	392-2024-00140102_XG_EN	Current version